



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued May 2011
Revised April 2014

| | | | |
|-------------------|---|--|-------------|
| Product: | R10-A01 | | |
| | <u>Metric</u> | <u>SAE</u> | |
| Style: | R10 | R10 | |
| Finish: | A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible) | A01 | |
| Weave: | Plain | Plain | |
| Construction | Warp: 16.0/10cm (+/- 1) Weft: 25 /10cm (+/- 1) | 4.1 /inch (+/- 0.3) 6.4 /inch (+/- 0.3) | ASTM D-3775 |
| Yarn | Warp: 1100 tex Weft: 735 tex | 450 yield 675 yield | |
| Weight | 356 g/m ² (+/-5%) | 10.5 oz/yd ² (+/-5%) | ASTM D-3776 |
| Thickness: | 0.40 mm (+/-0.3) | .016 inches (+/-0.004) | ASTM D-1777 |
| Packaging | | | |
| Core: | 77.01 mm ID Core | 3.0 inch ID Core | |
| Available Widths: | 1170 mm | 46 inch | |

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.