



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued: January 2013

Revised: April 2014

Product:	R11-A01		
	<u>Metric</u>	<u>SAE</u>	
Style:	R11	R11	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Plain	Plain	
Construction	Warp: 63/10cm (+/- 1) Weft: 55 /10cm (+/- 1)	16 /inch (+/- 0.3) ASTM D-3775 14 /inch (+/- 0.3)	
Yarn	Warp: 275 tex Weft: 275 tex	1800 yield 1800 yield	
Weight	375 g/m ² (+/-5%)	11.1 oz/yd ² (+/-5%)	ASTM D-3776
Thickness:	0.26 mm (+/-0.3)	0.01 inches (+/-0.004)	ASTM D-1777
Packaging			
Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	100 mm to 1520 mm	4 inch to 60 inch	

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.