



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued: June, 2004
Revised: April 2014

Product:	R11-A01		
	<u>Metric</u>	<u>SAE</u>	
Style:	R11	R11	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Plain	Plain	
Construction	Warp: 45.5/10cm (+/- 1) Weft: 45.5 /10cm (+/- 1)	11.6 /inch (+/- 0.3) 11.6 /inch (+/- 0.3)	ASTM D-3775
Yarn	Warp: 413 tex Weft: 413 tex	1200 yield 1200 yield	
Weight	375 g/m ² (+/-5%)	11.1 oz/yd ² (+/-5%)	ASTM D-3776
Thickness:	0.35 mm (+/-0.3)	0.014 inches (+/-0.004)	ASTM D-1777
Packaging			
Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	76 mm to 1980 mm	3 inch to 78 inch	

All values above are nominal and are to be used as guidelines.
Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.