



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued: October, 2002

Revised: April, 2014

Product:	R15-A01		
	<u>Metric</u>	<u>SAE</u>	
Style:	R15	R15	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Plain	Plain	
Construction	Warp: 27.0/10cm (+/- 1) Weft: 15.3 /10cm (+/- 1)	6.9 /inch (+/- 0.3) 3.9 /inch (+/- 0.3)	ASTM D-3775
Yarn	Warp: 1100 tex Weft: 1470 tex	450 yield 337 yield	
Weight	526 g/m ² (+/-5%)	15.5 oz/yd ² (+/-5%)	ASTM D-3776
Thickness:	0.50 mm (+/-0.1)	0.020 inches (+/-0.004)	ASTM D-1777
Packaging			
Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	25 mm to 1980 mm	3 inch to 78 inch	

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.