



# Georgian Bay Reinforcement Fabrics

## WOVEN ROVING PRODUCT SPECIFICATION

Issued: August, 2002  
Revised: April, 2014

Product:	<b>R24-A01</b> Can be made with E glass or ECR Glass		
	<u>Metric</u>	<u>SAE</u>	
Style:	R24	R24	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Plain	Plain	
Construction	Warp: 19.7 /10cm (+/- 1) Weft: 16.8 /10cm (+/- 1)	5.0 /inch (+/- 0.3) 4.3 /inch (+/- 0.3)	ASTM D-3775
Yarn	Warp: 2200 tex Weft: 2200 tex	225 yield 225 yield	
Weight	813 g/m <sup>2</sup> (+/-5%)	24 oz/yd <sup>2</sup> (+/-5%)	ASTM D-3776
Thickness:	0.75 mm (+/-0.3)	0.030 inches (+/-0.004)	ASTM D-1777
Packaging			
Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	76 mm to 1980 mm	3 inch to 78 inch	

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.