



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued: August, 2002
Revised: April 2014

Product:	R24TCR-A01		
	<u>Metric</u>	<u>SAE</u>	
Style:	R24TCR	R24TCR	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Plain	Plain	
Construction	Warp: 19.7 /10cm (+/- 1) Weft: 25 /10cm (+/- 1)	5.0 /inch (+/- 0.3) 6.4 /inch (+/- 0.3)	ASTM D-3775
Yarn	Type: Owens Corning Advantex Warp: 2200 tex Weft: 2200 tex	225 yield 225 yield	
Weight	993 g/m ² (+/-5%)	29 oz/yd ² (+/-5%)	ASTM D-3776
Thickness:	0.75 mm (+/-0.3)	0.030 inches (+/-0.004)	ASTM D-1777
Packaging			
Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	1270 mm	50 inch	

All values above are nominal and are to be used as guidelines.
Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.