



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued: January 2013
Revised: April 2014

Product: **R3-24-510-A01**

| | <u>Metric</u> | <u>SAE</u> | |
|-------------------|---|--|-------------|
| Style: | R3-24 | R3-24 | |
| Finish: | A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible) | A01 | |
| Weave: | 3 layer stitched | 3 layer stitched | |
| Construction | Warp: 20/10cm (+/- 1) Weft: 42 /10cm (+/- 1) | 5.0 /inch (+/- 0.3) 10.5/inch (+/- 0.3) | ASTM D-3775 |
| Yarn | Warp: 1100 tex Weft: 2 x 735 tex | 450 yield 2 x 675 yield | |
| Weight | 846 g/m ² (+/-5%) | 25 oz/yd ² (+/-5%) | ASTM D-3776 |
| Thickness: | 0.72 mm (+/-0.3) | 0.03 inches (+/-0.004) | ASTM D-1777 |
| Packaging | | | |
| Core: | 77.01 mm ID Core | 3.0 inch ID Core | |
| Available Widths: | 510 mm | 20 inch | |

All values above are nominal and are to be used as guidelines.
Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.