



# Georgian Bay Reinforcement Fabrics

## KEVLAR TAPE PRODUCT SPECIFICATION

Issued: June, 2004  
Revised: April 2014

Product:	<b>T0101-K</b>		
	<u>Metric</u>	<u>SAE</u>	
Style:	T0101	T0101	
Finish:	K-Kevlar	K-Kevlar	
Weave:	Plain	Plain	
Construction	Warp: 51.0 /10cm (+/- 4) Weft: 37.0 /10cm (+/- 4)	13.0 /inch (+/- 1) 9.4 /inch (+/- 1)	ASTM D-3775
Yarn	Warp: 158 tex Natural Kevlar Weft: 111 tex Natural Kevlar		
Weight	125 g/m <sup>2</sup> (+/-5%)	3.7 oz/yd <sup>2</sup> (+/- 5%)	ASTM D-3776
Thickness:	0.25 mm (+/-0.03)	0.01 inches (0.001)	ASTM D-1777
Available Widths:	25 mm to 350 mm	1 inch to 14 inch	

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.