



Georgian Bay Reinforcement Fabrics

WOVEN TAPE PRODUCT SPECIFICATION

Issued: October 2012
Revised: April 2014

Product:	T1800		
	<u>Metric</u>	<u>SAE</u>	
Style:	T1800	T1800	
Finish: (Silane Direct Size Yarn)	A00/01	A00/01	
Weave:	Plain	Plain	
Construction	Warp: 70 /10cm (+/- 4) Weft: 55 /10cm (+/- 4)	18 /inch (+/- 1) 14 /inch (+/- 1)	ASTM D-3775
Yarn	Warp: 275 tex roving Weft: 2 x 68 tex yarn	K18 roving 2 x G75 1/0 yarn	
Weight	270 g/m ² (+/-5%)	8 oz/yd ² (+/- 5%)	ASTM D-3776
Thickness:	0.24 mm (+/-0.05)	0.094 inches (0.002)	ASTM D-1777
Available Widths:	51 mm to 325 mm	2 inch to 13 inch	

All values above are nominal and are to be used as guidelines.

Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.

Georgian Bay Reinforcement Fabrics