



Georgian Bay Reinforcement Fabrics

WOVEN ROVING PRODUCT SPECIFICATION

Issued: December 2014
Reviewed: July 2023

Product: **R18B-A01**

	<u>Metric</u>	<u>SAE</u>	
Style:	R18B	R18B	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Plain	Plain	
Construction	Warp: 20.0/10cm (+/- 1) Weft: 20.0 /10cm (+/- 1)	5.0 /inch (+/- 0.3) 5.0 /inch (+/- 0.3)	ASTM D-3775
Yarn	Warp: 1500 tex Weft: 1500 tex	330 yield 330 yield	
Weight	600 g/m ² (+/-5%)	18 oz/yd ² (+/-5%)	ASTM D-3776
Thickness:	0.56 mm (+/-0.03)	0.022 inches (+/-0.004)	ASTM D-1777
Packaging			
Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	76 mm to 1980 mm	3 inch to 78 inch	

All values above are nominal and are to be used as guidelines.
Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.