

Issued October 2002

Woven Roving Product Specification

| | | | Revised January 2023 |
|--------------------|----------------|---|--|
| Product: | | R15-A01 | |
| | | <u>Metric</u> | SAE |
| Style: | | R15 | R15 |
| Finish: | | A01 (Polyester, Vinyl Ester, Epoxy | A01 and Acrylic Resin Compatible) |
| Weave: | | Plain | Plain |
| Construction | Warp: Weft: | 27.0/10cm (+/- 1) 15.3 /10cm (+/- 1) | 6.9 /inch (+/- 0.3) ASTM D-3775 3.9 /inch (+/- 0.3) |
| Yarn | Warp: Weft: | 1000 tex 1470 tex | 450 yield 337 yield |
| Weight | | 526 g/m² (+/-5%) | 15.5 oz/yd² (+/-5%) astm d-3776 |
| Thickness: | | 0.50 mm (+/-0.03) .C | 020 inches (+/-0.004) ASTM D-1777 |
| Packaging Core: | | 77.01 mm ID Core | 3.0 inch ID Core |
| Available Widths: | | 76 mm to 1980 mm | 3 inch to 78 inch |

All values above are nominal and are to be used as guidelines. Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.

Georgian Bay Reinforcement Fabrics