

Issued: August 2002

Woven Roving Product Specification

			Revised: January 2023
Product:		R24-A01	
		<u>Metric</u>	SAE
Style:		R24	R24
Finish:		A01 (Polyester, Vinyl Ester, Epoxy	A01 and Acrylic Resin Compatible)
Weave:		Hopsack/Basket	Hopsack/Basket
Construction	Warp: Weft:	19.7/10cm (+/- 1) 16.8 /10cm (+/- 1)	5.0 /inch (+/- 0.3) ASTM D-3775 4.3 /inch (+/- 0.3)
Yarn	Warp: Weft:	2200 tex 2200 tex	225 yield 225 yield
Weight		813 g/m² (+/-5%)	24 oz/yd² (+/-5%) ASTM D-3776
Thickness:		0.75 mm (+/-0.03) .C	030 inches (+/-0.004) ASTM D-1777
Packaging Core:		77.01 mm ID Core	3.0 inch ID Core
Available Widths:		76 mm to 1980 mm	3 inch to 78 inch

All values above are nominal and are to be used as guidelines. Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.

Georgian Bay Reinforcement Fabrics