



## Woven Roving Product Specification

Issued: August 2002  
Revised: January 2023

Product:	<b>R24CR-A01 Corrosion Resistance</b>		
	<u>Metric</u>	<u>SAE</u>	
Style:	R24CR	R24CR	
Finish:	A01 (Polyester, Vinyl Ester, Epoxy and Acrylic Resin Compatible)	A01	
Weave:	Hopsack/Basket	Hopsack/Basket	
Construction	Warp: 19.7/10cm (+/- 1) Weft: 16.8 /10cm (+/- 1)	5.0 /inch (+/- 0.3) 4.3 /inch (+/- 0.3)	ASTM D-3775
Yarn	Type: Owens Corning Advantex Warp: 2200 tex Weft: 2200 tex	225 yield 225 yield	
Weight	813 g/m <sup>2</sup> (+/-5%)	24 oz/yd <sup>2</sup> (+/-5%)	ASTM D-3776
Thickness:	0.75 mm (+/-0.03)	.030 inches (+/-0.004)	ASTM D-1777
Packaging Core:	77.01 mm ID Core	3.0 inch ID Core	
Available Widths:	76 mm to 1980 mm	3 inch to 78 inch	

*All values above are nominal and are to be used as guidelines.  
Although all statements are believed to be accurate and reliable, they are presented  
without guarantee or responsibility on our part.*