

Woven Roving Product Specification

Issued: August 2002 Revised: January 2023

Product:		R24TCR-A01 Tight Corrosion Resistant	
		<u>Metric</u>	SAE
Style:		R24TCR	R24TCR
Finish:		A01 (Polyester, Vinyl Ester, Epoxy	A01 and Acrylic Resin Compatible)
Weave:		Hopsack/Basket	Hopsack/Basket
Construction	Warp: Weft:	19.7/10cm (+/- 1) 25/10cm (+/- 1)	5.0/inch (+/- 0.3) ASTM D-3775 6.4/inch (+/- 0.3)
Yarn	Warp: Weft:	2200 tex 2200 tex	225 yield 225 yield
Weight		993 g/m² (+/-5%)	29 oz/yd² (+/-5%) ASTM D-3776
Thickness:		0.75 mm (+/-0.03) .C	30 inches (+/-0.004) ASTM D-1777
Packaging Core:		77.01 mm ID Core	3.0 inch ID Core
Available Widths:		1270 mm	50 inch

All values above are nominal and are to be used as guidelines. Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.

Georgian Bay Reinforcement Fabrics