

## Woven Tape – S glass Product Specification

Issued: December 2015 Revised: January 2023

| Product:          |                | T0605S-A02 S-glass                                  |   |
|-------------------|----------------|---|---|
|                   |                | <u>Metric</u>                                       | SAE   |
| Style:            |                | T0605S  | T0605S  |
| Finish:           |                | A02<br>(Epoxy Compatible)                           | A02<br>(Epoxy Compatible                                  |
| Weave:            |                | Plain   | Plain   |
| Construction      | Warp:<br>Weft: | 38/10cm (+/- 1)<br>34/10cm (+/- 1)                  | 9.7/inch (+/- 0.3) ASTM D-3775<br>8.6/inch (+/- 0.3)      |
| Yarn              | Warp:<br>Weft: | 403 tex S² glass roving<br>2 x 68 tex S² glass yarn | 1250 yield S² glass roving<br>2 x SCG75 1/0 S² glass yarn |
| Weight            |                | 200 g/m² (+/-5%)                                    | 6.0 oz/yd² (+/-5%) ASTM D-3776                            |
| Thickness:        |                | 0.2 mm (+/-0.03) .C                                 | 008 inches (+/-0.002) ASTM D-1777                         |
| Available Widths: |                | 25 mm to 350 mm                                     | 1 inch to 14 inch   |

All values above are nominal and are to be used as guidelines. Although all statements are believed to be accurate and reliable, they are presented without guarantee or responsibility on our part.

Georgian Bay Reinforcement Fabrics